EPE FOAM




EPE Foam Product Range

| Sr. No. | EPE Foam Roll |
|---------|--|
| 01 | 0.85 mm to 5 mm Single Layer Roll |
| 02 | 5 mm to 40 mm Multi Layer Roll |
| 03 | 15 mm to 100 mm Sheet |
| 04 | Natural EPE Foam Roll & Sheet |
| 05 | Antistatic EPE Foam Roll & Sheet |
| 06 | Fire Retardant EPE Foam Roll & Sheet |
| 07 | EPE Foam with HM HD Film Laminate Roll |

Available Colour:

White Black Pink Blue Green



EPE Foam Technical Specifications

| Sr. No. | Property | Unit | Value | Remarks |
|---------|------------------------------|---------------------|--------------------|-------------------|
| 01 | Density | kg/mtr3 | 20 | As per ISO:845 |
| 02 | Tear Strength | kg/cm | up to 0.7 | As per ISO:8067 |
| 03 | Tensile Strength | | | |
| | (a) Transverse Direction | kg/cm2 | 1.5 - 3.5 | IS:7888 |
| | (b) Machine Direction | kg/cm2 | 2.5 - 5.0 | -do- |
| 04 | Elongation at Break | | | |
| | (a) Transverse Direction | % | 50 - 70 | IS:7888 |
| | (b) Machine Direction | % | 80 - 100 | -do- |
| 05 | Compressive Strength at 10% | kg/cm2 | 0.08 - 0.20 | |
| 06 | Water absorption 96 hours at | % | 0.01 - 0.50 | |
| | 27°C working | | | |
| | Thermal conductivity at 50°C | k-cal/hr.m0C | 0.015 - 0.028 | As per ASTM C 177 |
| | mean temp. | | | |
| 08 | Chemical Resistance | | Excellent | |
| 09 | Fire Retardency | UL 94HF-1/2 | Self-Extinguishing | |
| | | FMVSS -302 | | |
| 10 | Basic Raw Material | LDPE (1020) FA 20 | | |
| 11 | Packaging | Woven Sacs Packing | | |
| 12 | Product using | Insulation, roofing | | |





GOLDCOIN FOAM PVT. LTD.





EPE Foam Applications

Ceramic products and sanitary wares Electronic equipments Handicrafts Submersible pumps Insulation Automobiles Marine Construction Jewelry packing Toys & novelties Mattress

Packaging

Fabrication Buffers

Mandap decoration Furniture industry

Roofing

Carpet & mats

Sports

All type of bags

Shoes

Floring

Cold storage

Tent house

Bus seat



EPE Foam Product Features:

Resillience, Cushioning, Shock Absorption, Flexibility, Abrasion, Resistance, Light Weight, Soft And Tough, Ease Of Fabrication/Lay, Water/Moisture Resistant, Chemically Inert, Oil Resistant, Non Toxic, Hygienic & Fungal Resistant, Thermal Insulation, Sound/Vibration Dampener, Wider Temperature Range, CFC Free

AIR BUBBLE FILM ROLL





Air Bubble Film Weight Chart

| Guage | GSM | Weight For 1 mtr Rools | Weight For 1.5 mtr Rools | Weight For 2 mtr Rools |
|-------|------|---------------------------|-----------------------------|---------------------------|
| 175 | 40 | 4.00 | 6.00 | 8.00 |
| 200 | 45 | 4.50 | 6.75 | 9.00 |
| 220 | 50 | 5.00 | 7.50 | 10.00 |
| 230 | 54 | 5.40 | 8.10 | 10.80 |
| 240 | 55 | 5.50 | 8.25 | 11.00 |
| 250 | 57.5 | 5.75 | 8.60 | 11.50 |
| 260 | 60 | 6.00 | 9.00 | 12.00 |
| 280 | 65 | 6.50 | 9.75 | 13.00 |
| 300 | 70 | 7.00 | 10.50 | 14.00 |
| 325 | 75 | 7.50 | 11.25 | 15.00 |
| 350 | 80 | 8.00 | 12.00 | 16.00 |
| 380 | 87 | 8.70 | 13.05 | 17.40 |
| 400 | 90 | 9.00 | 13.5 | 18.00 |
| 450 | 10.5 | 10.50 | 15.75 | 21.00 |
| 480 | 110 | 11.00 | 16.50 | 22.00 |
| 500 | 115 | 11.50 | 17.25 | 23.00 |
| 550 | 125 | 12.50 | 18.75 | 25.00 |
| 600 | 140 | 13.50 | 21.00 | 27.00 |
| 700 | 160 | 16.00 | 24.00 | 32.00 |
| 800 | 180 | 18.50 | 27.50 | 37.00 |

Air Bubble Film Technical Specifications

| Water Absorption | 0.02% after 24hrs | |
|-----------------------------|--------------------------|--|
| Chemical Resistance | Excellent | |
| Thermal Conductivity | Very Low | |
| Service Temperature | 8 degree C + 60 degree C | |
| Transparency | T – 90 % | |
| Tensile Elongation at break | More then 200% | |
| Bursting Strength- | More than 2500kg./cm cu | |
| Bubble Diameter | 10 mm | |
| Bubble Density | 8150 Nos/Sq mt. | |
| Maximum Width | 2.0 mtr | |
| Length Available | upto 100 mts. | |
| GSM AVAILBLE | 40 GSM to 180 GSM | |



GOLDCOIN FOAM PVT. LTD.





Air Bubble Film Applications

Used as protective packaging


Used by electronic and automobile industries

Majorly used in pouch forms by electronic, automobiles, furnitures and other industries to -protect fragile

Climatic hazards (moisture/dust)

Easy to carry, easy to dispense, easy to store, easy to display

Flexible & light weight packaging, easy for packing and un packing



Air Bubble Film Product Features:

- Transparent, hygienic, dust free & non toxic
- Can be easily wrapped around the product for cushioning
- Resistant to moisture
- Provides excellent surface protection against accidental impact & scratches
- Can be supplied in roll form or in customized fabricated forms such as pouches, cut pieces, wraparounds etc.
- Various laminates available such as foam, film (printed or unprinted)
- Environment friendly product. 100% recyclable



EPE FOAM NET



EPE Foam Net Product Range

| Sizes | Example Of Usage | |
|---------------------|----------------------------------|--|
| 50mm x 100mm | Mango, Apple, Peach, Pomegranate | |
| 50mm x 140mm | Mango, Apple, Peach, Pomegranate | |
| 50mm x 330mm | Papaya and Bottle | |
| 60mm x 100mm | Mango, Apple, Peach, Pomegranate | |
| 60mm x 140mm | Mango, Apple, Peach, Pomegranate | |
| 70mm x 150mm | Guava | |
| 40mm x 80mm x 180mm | Guava | |
| 50mm x 80mm x 220mm | Guava | |



GOLDCOIN FOAM PVT. LTD.



EPE Foam Net Applications

Fruit packaging

Vegetable packaging

Packaging of glass bottles



EPE Foam Net Product Features:

- Protection & decoration of your products
- Flexible and easy to use
- Hygienic and non toxic
- Economical and reusable
- Goods, especially suitable for fruits, bottles and other fragile products
- Make your fruits more eye catching, neat and deluxe
- Size and colour can customised
- Soft, light weight, non poisonous







Name : Mr. Mahesh Tilara

Designation: Director

Email : mahesh@goldcoinfoam.com

Mobile : +91 99241 28628

A thorough Technocrat, who has gained knowledge by handling various products and has achieved perfection in production process. His main responsibility lies in getting the production done with highest level of Quality Standards set, achieving the right product mix with optimum process parameters and product specifications. With his experience, Group has achieved the optimum productivity and minimal rejections.









For More Information Contact Us At

GOLDCOIN FOAM PVT. LTD.

Survey No. 79, National Highway 27, Village: Shapar, Dist. Rajkot - 360 024. (Gujarat) INDIA.

Mobile: +91 98243 62020 / 99099 55779 Email: info@goldcoinfoam.com

Web: www.goldcoinfoam.com | www.goldcoineps.com

EPE Foam / Air Bubble Film / EPE Foam Net Inquiries Please Contact

Contact Person: Mrs. Sasmita BarikMiss Kajal DhrangdhriyaDesignation: (G.M. Marketing)(Marketing Executive)Email: sales@goldcoinfoam.comkajal@goldcoinfoam.comMobile: +91 99241 24024+91 99789 76307

EPS Disposable Inquiries Please Contact

Contact Person: Mr. Dibyendu SircarMr. Gautam BhuvaDesignation: G.M. Marketing(Marketing Executive)Email: sales@goldcoineps.cominfo@goldcoineps.comMobile: +91 99789 76308+91 99241 44455